

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Consommation  
et Corporations Canada

Consumer and  
Corporate Affairs Canada (21) (A1)

2,062,635

Bureau des brevets

Patent Office (22)

1992/03/11

Ottawa, Canada  
K1A 0C9

(43)

1993/09/12

5,005,6/75

(51) INTL.CL.<sup>5</sup> A63B-059/14

---

(19) (CA) **APPLICATION FOR CANADIAN PATENT** (12)

(54) Method for Producing an Ice Hockey Stick and the Product  
Therefor

(72) Lo, Kun-Nan - Taiwan ;

(73) Same as inventor

(57) 13 Claims

Notice: The specification contained herein as filed

**Canada**

## ABSTRACT OF THE DISCLOSURE

A method for producing an ice hockey stick includes

---

the steps of forming an upper and a lower preform;  
wrapping an impregnated fiber laminate around the upper  
5 and lower preforms respectively; withdrawing the upper  
and lower preforms to form hollow upper and lower  
 housings; passing an inflatable tube member through the  
upper and lower housings; disposing the upper housing  
on the lower housing and wrapping the impregnated fiber  
10 laminate around the upper and lower housings to form a  
fiber impregnated blade housing; inflating the tube  
member and heating the fiber impregnated blade housing  
in a mold to form a green blade section having a  
transverse reinforcing rib; removing the tube member  
15 from the green blade section and finishing the green  
blade section; and connecting the finished green blade  
section to a shaft section.

METHOD FOR PRODUCING AN ICE HOCKEY STICK AND THE  
PRODUCT THEREOF

BACKGROUND OF THE INVENTION

---

1. Field of the Invention

5           This invention relates a method for producing an ice hockey stick and the product thereof, more particularly to a method for producing an ice hockey stick which is made of impregnated fiber laminates and which has a transverse reinforcing rib formed in the  
10       blade of the ice hockey stick.

2. Description of the Related Art

          Conventionally, ice hockey sticks are made of wood. Referring to Fig. 1, a conventional wooden ice hockey stick includes a blade (1) formed by laminating and  
15       adhering a plurality of wood strips (1a), a curve portion (2) which is formed by laminating a plurality of wood strips (2a) in a manner similar to the fabrication of the blade (1) and a shaft (3) adhered to the curve portion (2). The curve portion (2) must be  
20       heated so as to be bent manually. Therefore, manufacturing of such a wooded ice hockey stick is a troublesome process and precise bending of the curve portion (2) is difficult to achieve. In addition, such a wooded ice hockey stick is likely to break along the  
25       seams between the wood strips (1a) and (2a). Hence, the wooden ice hockey stick is not durable.

SUMMARY OF THE INVENTION

It is a feature of this invention to provide a method for producing an ice hockey stick which is easy to manufacture and which makes it easy to obtain high quality and precise bending of the curve portion.

5 It is another feature of this invention to provide an ice hockey stick which is durable.

Accordingly, the method for producing an ice hockey stick provided by this method of this invention has a shaft section and a blade section which includes a blade and a curve interconnecting the blade and the  
10 shaft section, the method comprising the steps of:

forming an upper and a lower preform which are shaped as an upper and lower half portion of the blade section of the ice hockey stick;

15 wrapping an impregnated fiber laminate around said upper and lower preforms respectively;

withdrawing said upper and lower preforms so as to form a hollow upper and lower housing each of which has a front and a rear open end;

20 passing an inflatable tube member with a closed end through the upper and lower housings;

disposing the upper housing on the lower housing and wrapping the impregnated fiber laminate around the upper and lower housings to form a fiber impregnated  
25 blade housing which encloses the front open ends of the upper and lower housings;

inflating the tube member in the upper and lower

housings and heating the fiber impregnated blade housing in a mold for a predetermined period to form a green blade section having a transverse reinforcing rib

---

---

which is integrally formed by an overlapping portion of the upper and lower housings;

removing the tube member from the green blade section and finishing the green blade section; and

connecting the finished green blade section to the shaft section.

Since, the ice hockey stick of this invention is formed by a molding process, the bending angle of the curve portion can be precisely controlled. In addition, the ice hockey stick of this invention is made of impregnated fiber laminates which is durable for impacting and striking.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Other features and advantages of this invention will become apparent in the following detailed description of the preferred embodiments of this invention with reference to the accompanying drawings, in which:

Fig. 1 is a fragmentary exploded side view of a conventional wood ice hockey stick;

Fig. 2 is a flow diagram of the method for producing a preferred embodiment of an ice hockey stick of this invention;

Fig. 3 is a side schematic view of a preferred

embodiment of the upper and lower preforms of the blade section of an ice hockey stick of this invention;

Fig. 4 is a side schematic view showing the preferred embodiment of the upper and lower preforms of the blade section of this invention which are wrapped with impregnated fiber laminates to form an upper and lower housing;

Fig. 5 is a side schematic view showing the preferred embodiment of the upper and lower housings of the blade section of this invention which are connected to one another and which have a tube member passing through;

Fig. 6 is a side schematic view showing the preferred embodiment of the upper and lower housings being wrapped by a impregnated fiber laminate and the tube member being inflated;

Fig. 7 is a side view showing the cross-sections of the blade section of the ice hockey stick of this invention at four positions;

Fig. 8 is a side schematic view showing the preferred embodiment of the ice hockey stick of this invention; and

Fig. 9 is a side schematic view showing another preferred embodiment of the blade section of an ice hockey stick of this invention having a striking mark formed thereon.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring to Fig. 2, a flow diagram of a method for producing an ice hockey stick of this invention is shown. An upper and lower preform (10, 10') with

proper thickness are prepared as shown in Fig. 3. The  
5 upper and lower preforms (10, 10') are made of wood, plastic, or metal plate and are shaped as an upper and lower half portion of a blade section of an ice hockey stick, as shown in block 1. Two to five layers of impregnated carbon fibers are wrapped around the upper  
10 and lower preforms (10, 10') respectively to form an impregnated fiber laminate with a desired thickness, as shown in Fig 4. Other types impregnated fibers, such as impregnated glass fibers, may also be used. The carbon fibers may be wrapped at an intersection angle  
15 of 0°, 30°, 45°, 90° or the combination thereof, as shown in block 2. The upper and lower preforms (10, 10') are then withdrawn from the upper and lower housing (20, 20'), as shown in block 3. Thus, a hollow upper and lower housing (20, 20') is formed around the  
20 upper and lower preforms (10, 10'). Each of the upper and lower housings has a front and rear open end [(21, 22), (21', 22')], as shown in Fig. 5.

An inflatable tube member (30) with a closed end (31) passes from the open rear end (22) of the hollow  
25 upper housing (20) through the open front end (21) of the hollow upper housing (20), the open front end (21') of the hollow lower housing (20') and out of the open



rear end (22') of the hollow lower housing (20'), as shown in block 4. The tube member (30) is made of oriented propylene or nylon. The upper housing (20) is then disposed on the lower housing (20'), as shown in block 5. The outline of the combination of the upper and lower housing is similar to that of the blade section of the ice hockey stick, as best illustrated in Fig. 5.

The overlapped upper and lower housings (20, 20') are wrapped by impregnated carbon fibers so as to form a fiber impregnated blade housing (40) in a manner similar to the wrapping of the preforms (10, 10'), as shown in block 6. The fiber impregnated blade housing 40 encloses the front open ends (21, 21') of the upper and lower housings (20, 20'). The tube member (30) is inflated with air having an air pressure of 4-10 kg/cm<sup>2</sup> and the fiber impregnated blade housing (40) is heated in a mold for about 30-60 minutes, as shown in block 7. A green blade section having a transverse reinforcing rib (50) is integrally formed by an overlapping portion of the upper and lower housings (20, 20'), as shown in Fig. 7. The transverse reinforcing rib (50) has a width gradually increasing from the front end toward the rear end of the green blade section, as best illustrated in the cross-sections at four different positions of Fig. 7. The tube member (30) is then removed from the green blade section, and thereby

forming a hollow green blade which includes a blade (60) and a shank (70) connected to the blade 60 are formed, as shown in block 8. The hollow green blade section is finished, as shown in block 9. A foamed material may fill in the hollow green blade to increase its shock-absorbing ability. A hollow shaft section (80) is connected to the finished green blade section by a hot melt glue (81), as shown in block 10. Thereby, when the shank (70) of the blade section is cracked and/or broken, the user can heat the hot melt glue (81) so as to melt the same in order to separate the shaft section (80) from the blade section and connected a new blade section to the shaft section (80) by means of the hot melt glue (81). The shaft section (80) is made of an aluminum alloy or carbon fiber. The free end of the shaft section (80) is connected to a handle and an ice hockey stick of this invention is thus obtained, as best illustrated in Fig. 8. To increase the binding strength of the shank (70) and the shaft section (80), grooves (72) are formed on the shank (70) and projections (not shown) are correspondingly formed on the inside face of the hollow shaft section (80). A striking mark (61) may be provided on the face of the blade (60), as shown in Fig. 9. The striking mark (61) may be in the form of slots, studs or ridges.

Therefore, an ice hockey stick of this invention

can be formed by a molding process and the bending angle of the curve portion can be precisely controlled.

The obtained ice hockey stick, which is made of

---

---

impregnated fiber laminates, is light-weight and is

5 durable for impacting and striking because of the transverse reinforcing rib. The reinforcing rib of the ice hockey stick also increases the rigidity and recovery coefficient of striking of the blade section. Thus, the contacting time between the blade section and  
10 the puck is reduced, thereby increasing the bursting power of striking.

With this invention thus explained, it is apparent that numerous modifications and variations can be made without departing from the scope and spirit of this  
15 invention. It is therefore intended that this invention be limited only as indicated in the appended claims.

I CLAIM:

1. A method for producing an ice hockey stick having a  
~~shaft section and a blade section which includes a~~  
blade and a curve interconnecting said blade and said  
5 shaft section, said method comprising the steps of:  
    forming an upper and a lower preform which are  
shaped as an upper and lower half portion of said blade  
section of said ice hockey stick;  
    wrapping an impregnated fiber laminate around said  
10 upper and lower preforms respectively;  
    withdrawing said upper and lower preforms so as to  
form a hollow upper and lower housing each of which has  
a front and a rear open end;  
    passing an inflatable tube member with a closed end  
15 through said upper and lower housings;  
    disposing said upper housing on said lower housing  
and wrapping said impregnated fiber laminate around  
said upper and lower housings to form a fiber  
impregnated blade housing which encloses said front  
20 open ends of said upper and lower housings;  
    inflating said tube member in said upper and lower  
housings and heating said fiber impregnated blade  
housing in a mold for a predetermined period to form a  
green blade section having a transverse reinforcing rib  
25 which is integrally formed by an overlapping portion of  
said upper and lower housings;  
    removing said tube member from said green blade

section and finishing said green blade section; and

connecting said finished green blade section to

---

~~said shaft section.~~

---

2. A method for producing an ice hockey stick as  
5 claimed in Claim 1, wherein each of said upper and  
lower preforms has a thickness of 1.5 to 5 mm.

3. A method for producing an ice hockey stick as  
claimed in Claim 1, wherein said impregnated fiber  
laminate is made of impregnated carbon fibers.

10 4. A method for producing an ice hockey stick as  
claimed in Claim 1, wherein said impregnated fiber  
laminate is made of impregnated glass fibers.

5. A method for producing an ice hockey stick as  
claimed in Claim 1, wherein said inflatable tube member  
15 is made of nylon.

6. A method for producing an ice hockey stick as  
claimed in Claim 1, wherein said inflatable tube member  
is made of oriented propylene.

7. A method for producing an ice hockey stick as  
20 claimed in Claim 1, wherein said inflatable tube member  
is inflated with a gas pressure of 4 to 10 Kg/cm<sup>2</sup> and  
said predetermined period of said heating step is 30 to  
60 minutes.

8. A method for producing an ice hockey stick as  
25 claimed in Claim 1, wherein said connecting steps  
includes connecting said finished green blade section  
to said shaft section by means of a hot melt glue.

9. A method for producing an ice hockey stick as claimed in Claim 1 further including the step of forming a striking mark on said blade.

---

5 10. A method for producing an ice hockey stick as claimed in Claim 1 further including the step of providing a foamed material in said green blade section.

10 11. An ice hockey stick comprising a shaft section and a hollow blade section connected to said shaft section, said blade section being made of an impregnated fiber and having a transverse reinforcing rib formed therein.

12. An ice hockey stick as claimed in Claim 11, wherein a hot melt glue is provided to said shaft and said hollow blade sections.

15 13. An ice hockey stick as claimed in Claim 11, wherein said hollow blade section is filled with a foamed material.




FIG. 1  
PRIOR ART






FIG. 2






FIG.3




FIG.4





FIG. 5






FIG. 8




FIG. 9